



# Cromarod 312

SMAW - (Stick) - MMA  
Stainless Steel

Date: 2013-10-21  
Revision: 20


### Description:

Cromarod 312 is a rutile flux coated electrode which deposits a 29%Cr / 9%Ni austenitic/ferritic stainless steel weld metal with a ferrite content of approximately FN 50. The weld metal exhibits excellent tolerance to dilution from dissimilar and difficult-to-weld materials without hot cracking.

### Applications:

- Difficult-to-weld steels e.g. high carbon hardenable tool, die and spring steels, 13% Mn steels, free-cutting steels, high temperature steels (non-structural).
- Dissimilar joints between stainless and high carbon steels.
- Surfacing of metal-to-metal wear areas, hot working tools, furnace components.

### Welding positions:



### Coating type:

Rutile

### Welding current:

DC+, AC OCV > 39V

### Ferrite content:

FN 50 (WRC-92)

### Corrosion resistance

Good resistance to sulphurous gases at high temperature. Good resistance to wet corrosion up to approximately 300 °C.

### Scaling temperature:

Approx. 1100 °C in air.

### Redrying temperature:

350 °C, 2h

### Chemical composition, wt.%

	C	Si	Mn	P	S	Cr	Ni
Min			0,5			28,0	8,0
Typical	0,10	1,2	0,8	0,02	0,02	29,0	9,0
Max	0,15	1,3	2,0	0,035	0,025	31,0	10,5

	Mo	Cu	V	Nb
Min				
Typical	0,2			
Max	0,5	0,5	0,1	0,1

### Mechanical properties

	<u>Specified</u>	<u>Typical</u>
Yield strength, Rp0.2%:	≥ 450 MPa	590 MPa
Tensile Strength, Rm:	≥ 660 MPa	760 MPa
Elongation, A5	≥ 22%	25%

### Classification:

AWS A5.4 ~E 312-17  
ISO 3581-A E 29 9 R 32

### Approvals:

CE

### Note

All classifications: slight deviation in Si.

Core wire:  
P ≤ 0.030%  
S ≤ 0.030%  
N ≤ 0.080%

### Produkt data:

Diam.mm	Length mm	Product code	Current A	Voltage V	Kg weld metal/ kg electrodes	No. of electrodes/ kg weld metal	Kg weld metal/ hour arc time	Burn-off time/ electrode (sec.)
2,5	300	74382500	40-80	25	0,64	90	1,1	34
3,2	350	74383200	80-120	26	0,64	47	1,5	44
4,0	350	74384000	100-160	27	0,65	31	2,1	55

